



NATURHOLZPLATTEN

# 3-layer old wood spruce panel



The old wood spruce panel has a 3-layer structure. The old wood spruce panel receives its unique character from many irregularities and features in its overall appearance.



\*AHZ

the following is permissible: Strong and pronounced wood texture, pitch pockets, black branches, patched branches, colour differences, small imperfections, worm damage, cracks, nail holes, mechanical slat damage;

(1) Cracks (2) Nail holes (3) Discolouration (4) Worm damage



<b>Quality class</b>	AHZ*/Cgd sanded AHZ/AHZ on both sides upon request
<b>Middle layer</b>	Spruce
<b>Back layer</b>	Cgd, steamed spruce with no special quality requirements
<b>Lengths</b>	Mixed 2250 mm, 2500 mm, 3000 mm, 3500 mm, 4000 mm, 4500 mm, 5000 mm
<b>Width</b>	1250 mm
<b>Panel thickness</b>	19 mm (others upon request)
<b>Top layer thickness</b>	5,5 mm
<b>Top layer widths</b>	Mixed from 80 mm – 250 mm
<b>Technical class</b>	SWP/1 NS L3
<b>Surface treatment</b>	Brushing upon request

## TILLY Holzindustrie GmbH

Krappfelder Straße 27, 9330 Althofen/Austria

tel.: +43 4262 2143, fax: +43 4262 4144

office.platten@tilly.at, [www.tilly.at](http://www.tilly.at)

Subject to changes!